

## CP 066

Fade out thinner



**CP 066** thinner for shading two-component products is used for double- and single-layer technique of painting car bodies to perform a touch-up (painting a car partially) with a **Acryl** pigment or a colorless coat.

Most often used with narrow areas of certain elements (e.g. posts)

Can also be used for smart type of repair.

Packaging	
Unit	Collective (box)
1 L	6 pcs



**70 parts of thinner CP 066,**  
**30 parts of dwukomponentowy (2K).**



Apply one layer in several centimeter long stripes.  
The best effect is achieved with a small addition of a top coat.  
After drying it requires polishing.  
Spray gun\*. Gravity nozzle: **1,2-1,4 mm**. Suction nozzle: **1,4-1,6 mm**.  
Operating pressure - high pressure: **3-4 bar\***; HVL P: **2 bar\***.

\* Use high pressure equipment and HVL P. Pressure as recommended by the gun manufacturer.



Evaporation before applying consecutive layers: **3-4 min.**



Drying time 20°C, 65% H.R.:  
**10-20 min.**

### Surface preparation:

Miejsce przejścia matujemy papierem gradacją 1500-2000, lub szarą włókniną razem z pastą matującą. Powierzchnię odtłuszczamy zmywaczem CP 015.

### Recommended sizes of paint strainers:

190 µm

### Spray viscosity in 20°C:

11-12 s DIN Cup 4 mm

### Date of minimum durability:

24 months (in the original unopened package)

The recipe of the product complies with the VOC guidelines. The products supplied by our company are subject to a number of factory tests, so they can meet the highest demands. However, be aware of the individual conditions of storage, preparation and applications that can influence on the effect of varnishing. The guarantee to keep the highest quality of the coating is to use the product only with the products of the Manufacturer and in accordance with the recommendations of the Manufacturer. The Manufacturer does not guarantee performance and compatibility of the Products with products other than those of the Manufacturer. In order to recognize the guarantee and all claims, the user shall use the technologies and techniques for given Products - according to the technical data sheet and execute the sample spray prior to target painting.